

European Technical Assessment



Łukasiewicz
Instytut Ceramiki
i Materiałów
Budowlanych





Łukasiewicz
Instytut Ceramiki
i Materiałów
Budowlanych

02-676 Warsaw,
POLAND
Postępu Str. 9
Tel.: +48 22 843 74 21
info@icimb.pl
www.icimb.pl



European Technical Assessment

ETA-20/0345
of 05/05/2020

General Part

Technical Assessment Body issuing the European Technical Assessment:
Łukasiewicz – ICiMB

Trade name of the construction product	SOLTHERM 75
Product family to which the construction product belongs	External Thermal Insulation Composite Systems (ETICS) with rendering
Manufacturer	BOLIX SA Stolarska 8 34-300 Żywiec, POLAND www.bolix.pl
Manufacturing plant	BOLIX SA Stolarska 8 34-300 Żywiec, POLAND www.bolix.pl
This European Technical Assessment contains	17 pages including 3 Annexes which form an integral part of this assessment. Annex No 4 Control Plan contains confidential information and is not included in the European Technical Assessment when that assessment is publicly disseminated.
This European Technical Assessment is issued in accordance with Regulation (EU) No 305/2011, on the basis of	ETAG 004 used as EAD, 2013

Corrigendum

Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and should be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full (excepted the confidential Annex referred to above). However, partial reproduction may be made, with the written consent of the issuing Technical Assessment Body. Any partial reproduction has to be identified as such.

Specific part

1. Technical description of the product

This product SOLTHERM 75 is an ETICS (External Thermal Insulation Composite System with rendering) - a kit comprising components which are factory-produced by the manufacturer or component suppliers. The ETICS manufacturer is ultimately responsible for all components of the ETICS specified in this ETA.

The ETICS kit comprises a prefabricated insulation product of mineral wool (MW) to be bonded or mechanically fixed onto a wall. The method of fixing and the relevant components are specified in Table 1. The insulation product is faced with a rendering system consisting of one or more layers (site applied), one of which contains reinforcement. The rendering is applied directly to the insulating panels, without any air gap or disconnecting layer.

The ETICS may include special fittings (e.g. base profiles, corner profiles, expansion strips, tapes and sealing strips) to treat details of ETICS (connections, apertures, corners, parapets, sills, joinery) and elements to be strengthened, e.g. additional appropriately shaped fiberglass mesh stripes. Assessment and performance of these components is not addressed in this ETA, however the ETICS manufacturer is responsible for adequate compatibility and performance within the ETICS when the components are delivered as a part of the kit.

Table 1.

	Components	Coverage (kg/m ²)	Thickness (mm)
	Bonded ETICS; fully bonded or fully bonded with supplementary mechanical fixings. National application documents shall be taken into account.		
Insulation materials with associated methods of fixing	<ul style="list-style-type: none"> • Insulation product: mineral wool (MW) lamella according to EN 13162 <i>Product characteristics - see Annex No 1</i> 	-	50 to 300
	<ul style="list-style-type: none"> • Adhesives: - SOLTHERM MA S75 cement based powder requiring addition of 0,19-0,21 l/kg of water - SOLTHERM MB S75 cement based powder requiring addition of 0,20-0,22 l/kg of water 	about 5,0 (powder)	-
	<ul style="list-style-type: none"> • Supplementary mechanical fixings: Plastic anchors covered by relevant ETA with subtending plates of 140 mm diameter 	-	-

Table 1. cont.

	Components	Coverage (kg/m ²)	Thickness (mm)
Mechanically fixed ETICS (through insulation product) with supplementary adhesive. National application documents shall be taken into account.			
Insulation materials with associated methods of fixing	<ul style="list-style-type: none"> Insulation product: mineral wool (MW) standard and double density boards according to EN 13162 <i>Product characteristics - see Annex No 1</i> 	-	50 to 300* 110 to 300**
	<ul style="list-style-type: none"> Supplementary adhesives: <ul style="list-style-type: none"> - SOLTHERM MA S75 cement based powder requiring addition of 0,19-0,21 l/kg of water - SOLTHERM MB S75 cement based powder requiring addition of 0,20-0,22 l/kg of water 	about 5,0 (powder)	-
	<ul style="list-style-type: none"> Anchors <i>Products characteristics - see Annex No 2</i> 	-	-
Mechanically fixed ETICS (through reinforcement) with supplementary adhesive. National application documents shall be taken into account.			
Insulation materials with associated methods of fixing	<ul style="list-style-type: none"> Insulation product: mineral wool (MW) standard and double density boards according to EN 13162 <i>Product characteristics - see Annex No 1</i> 	-	50 to 300
	<ul style="list-style-type: none"> Supplementary adhesives: <ul style="list-style-type: none"> - SOLTHERM MA S75 cement based powder requiring addition of 0,19-0,21 l/kg of water - SOLTHERM MB S75 cement based powder requiring addition of 0,20-0,22 l/kg of water 	about 5,0 (powder)	-
	<ul style="list-style-type: none"> Anchors <i>Products characteristics - see Annex No 2</i> 	-	-

* standard boards and double density boards characteristics of wind load resistance according to table 9

** double density boards characteristics of wind load resistance according to table 10

Table 1. cont.

	Components	Coverage (kg/m ²)	Thickness (mm)
Base coat	<ul style="list-style-type: none"> • SOLTHERM MB S75 cement based powder requiring addition of 0,20-0,22 l/kg of water 	about 4,0 (powder)	3,0 to 5,0 or 4,0 to 6,0*
Reinforcement	<ul style="list-style-type: none"> • Standard glass fibre meshes applied in one or two layers - SOLTHERM HD 158/S - SOLTHERM HD 160/S - SOLTHERM HD 174/S - SOLTHERM HD 335/P <p><i>Products characteristics - see Annex No 3</i></p>	- - - -	- - - -
Key coat	<ul style="list-style-type: none"> • SOLTHERM SNP COLOUR S75 ready to use liquid to be used with finishing coat SOLTHERM SFC-P 15 S75 	0,25 to 0,40	-
	<ul style="list-style-type: none"> • SOLTHERM SNP / SOLTHERM SNP eco-shield ready to use liquid to be used with finishing coat SOLTHERM STC-P 	0,10 to 0,20	-
Finishing coats	<ul style="list-style-type: none"> • Silicone finishing coat SOLTHERM SFC-P 15 S75 ready to use pastes – silicone and acrylic binder floated structure max. particles size: 1,5 mm 	about 2,5	Regulated by particles size
Decorative coat	<ul style="list-style-type: none"> • SOLTHERM STC-P / SOLTHERM STC-P eco-shield ready to use liquid to be used optionally with finishing coat SOLTHERM SFC-P 15 S75 	0,18 to 0,28 l/m ²	-
Ancillary materials	<ul style="list-style-type: none"> • Setting accelerator SOLTHERM 4 SEASONS, ready to use liquid to be used optionally with finishing coat • Remain under the manufacturer's responsibility 		

*depending on number of applied layers of glass fibre meshes

2. Specification of the intended use in accordance with the applicable European Assessment Document (hereinafter EAD)

This ETICS is intended for use as external insulation of buildings' walls. The walls are made of masonry (bricks, blocks, stones) or concrete (cast on site or as prefabricated panels).

The ETICS can be used on new or existing (retrofit) vertical walls. It can also be used on horizontal or inclined surfaces which are not exposed to precipitation.

The ETICS is made of non load-bearing construction elements. It does not contribute directly to the stability of the wall on which it is installed, but it can contribute to durability by providing enhanced protection from the effect of weathering.

The ETICS is not intended to ensure the airtightness of the building structure.

The provisions made in this European Technical Assessment are based on an assumed working life of the ETICS of at least 25 years, provided that the requirements for the packaging, transport, storage, installation as well as appropriate use, maintenance and repair are met. The indication given on the working life cannot be interpreted as a guarantee given by the manufacturer or the Technical Assessment Body, but should only be regarded as a means for choosing the appropriate products in relation to the expected, economically reasonable working life of the works.

Design, installation, maintenance and repair of ETICS shall be done in accordance with principles introduced in chapter 7 of ETAG 004, used as EAD, and shall be in conformity with Member States' legislation requirements.

The instructions regarding packaging, transport, storage and installation of ETICS are specified in the manufacturer's technical documentation.

3. Performance of the product and references to the methods used for its assessment

The performances of the kit as described in this chapter are valid provided that the components of the kit comply with Annexes 1÷3.

3.1. Safety in case of fire (BWR 2)

3.1.1. Reaction to fire (ETAG 004: clause 5.1.2.1, EN 13501-1)

Table 2.

Configuration	Max. heat of combustion [MJ/kg]	Flame retardant content	Euroclass acc. to EN 13501-1
Adhesive	0,3	No flame retardant	A2-s1, d0
MW boards* <i>density ≤ 130 kg/m³</i>	-		
Base coat	0,3		
Glass fibre mesh	8,6		
Key coat	5,7		
Finishing coat	2,7		
Key coat	3,9		
Decorative coat	3,0		
*organic content in quantity ensuring Euroclass A1 according to EN 13501-1			

Note: European reference fire scenario has not been laid down for facades. In some Member States, the classification of ETICS according to EN 13501-1 might not be sufficient for the use in facades. An additional assessment of ETICS according to national provisions might be necessary to comply with Member State regulations, until the existing European classification system has been completed.

3.2. Hygiene, health and environment (BWR 3)

3.2.1. Water absorption (ETAG 004: clause 5.1.3.1)

- Base coat SOLTHERM MB S75:
 - Water absorption after 1 hour < 1 kg/m²;
 - Water absorption after 24 hours < 0,5 kg/m².
- Rendering system: Table 3.

Table 3.

	Water absorption after 24 hours	
	<0,5 kg/m ²	≥0,5 kg/m ²
Rendering system: base coat <u>SOLTHERM MB S75</u> + key coat <u>SOLTHERM SNP colour S75</u> + finishing coat <u>SOLTHERM SFC-P 15 S75</u>	x	-

3.2.2. Watertightness (ETAG 004: clause 5.1.3.2)

3.2.2.1. Hygrothermal behaviour (ETAG 004: clause 5.1.3.2.1)

Pass (without defects).

3.2.2.2. Freeze-thaw behaviour (ETAG 004: clause 5.1.3.2.2)

ETICS is frost resistant according to water absorption test.

3.2.3. Impact resistance (ETAG 004: clause 5.1.3.3)

Table 4.

<p>Rendering system: base coat <u>SOLTHERM MB S75</u> + key coat SOLTHERM SNP colour S75 + finishing coat SOLTHERM SFC-P 15 S75</p>	Single layer of standard mesh
	MW board acc. to Annex No 1
	Category II
	MW double density acc. to Annex No 1
	Category II
	MW lamella acc. to Annex No 1
	Category II

3.2.4. Water vapour permeability (ETAG 004: clause 5.1.3.4)

Table 5.

		Average equivalent air thickness s_d
<p>Rendering system: base coat <u>SOLTHERM MB S75</u> + key coat SOLTHERM SNP colour S75 + finishing coat + key coat + decorative coat (if used)</p>	<u>SOLTHERM SFC-P 15 S75</u>	≤ 1 m, result: 0,3 m
	<u>SOLTHERM SFC-P 15 S75</u> + SOLTHERM SNP / SOLTHERM SNP eco-shield + SOLTHERM STC-P / SOLTHERM STC-P eco-shield	≤ 1 m, result: 0,5 m

3.2.5. Release of dangerous substances (ETAG 004: clause 5.1.3.5, EOTA TR034)

No performance assessed.

Note: There may be requirements applicable to the ETICS falling within its scope (e.g. transposed European legislation and national laws, regulations and administrative provisions). In order to meet the provisions of the Regulation (EU) No 305/2011, these requirements need to be complied with, when and where they apply.

3.3. Safety and accessibility in use (BWR 4)

3.3.1. Bond strength between base coat and insulation product (ETAG 004: clause 5.1.4.1.1)

Base coat: SOLTHERM MB S75

- Initial state and after hygrothermal cycles:

≥ 0,08 MPa or failure into mineral wool

3.3.2. Bond strength between adhesive and substrate (ETAG 004: clause 5.1.4.1.2)

Table 6.

	Initial state	48 h immersion in water + 2 hours 23°C/50% RH	48 h immersion in water + 7 days 23°C/50% RH
SOLTHERM MA S75	≥ 0,80 MPa	≥ 0,60 MPa	≥ 0,90 MPa
SOLTHERM MB S75	≥ 0,80 MPa	≥ 0,60 MPa	≥ 0,90 MPa

3.3.3. Bond strength between adhesive and insulation product (ETAG 004: clause 5.1.4.1.3)

Table 7.

	Initial state	48 h immersion in water + 2 hours 23°C/50% RH	48 h immersion in water + 7 days 23°C/50% RH
SOLTHERM MA S75	≥ 0,08 MPa*	≥ 0,03 MPa*	≥ 0,08 MPa*
SOLTHERM MB S75			

*failure into mineral wool

3.3.4. Bond strength after ageing (ETAG 004: clause 5.1.7.1)

Table 8.

	After hygrothermal cycles
Rendering system: base coat <u>SOLTHERM MB S75</u> + key coat <u>SOLTHERM SNP colour S75</u> + finishing coat <u>SOLTHERM SFC-P 15 S75</u>	MW board acc. to Annex No 1 ≥ 0,01 MPa*
	MW double density acc. to Annex No 1 ≥ 0,01 MPa*
	MW lamella acc. to Annex No 1 ≥ 0,08 MPa*

*failure into mineral wool

3.3.5. Fixing strength (ETAG 004, clause 5.1.4.2)

Test not required. ETICS fulfils the criteria $E \cdot d \leq 50\,000$ N/mm.

3.3.6. Wind load resistance (ETAG 004, clause 5.1.4.3)

Table 9.

Anchors for which the following failure loads apply		Anchors according to Annex No 2*	
		Plate diameter (mm)	≥ 60
Characteristics of the MW boards and MW double density boards for which the following failure loads apply		Thickness (mm)	≥ 50
		Tensile strength perpendicular to the faces (kPa)	≥ 10
Failure loads (N)	Anchors not placed at the panel joints (<i>Pull-through test</i>) dry conditions	R_{panel}	Minimum: 263 Average: 317
	Anchors not placed at the panel joints (<i>Pull-through test</i>) wet conditions	R_{panel}	Minimum: 288 Average: 336
	Anchors placed at the panel joints (<i>Pull-through test</i>) dry conditions	R_{joint}	Minimum: 182 Average: 277
	Anchors placed at the panel joints (<i>Pull-through test</i>) wet conditions	R_{joint}	Minimum: 155 Average: 215
	Anchors placed at the panel joints (<i>Static foam block test</i>)	R_{joint}	Minimum: 1120 Average: 1170

*plate stiffness of anchors fixed through reinforcement shall be equal to or higher than 0,6 kN/mm

Table 10.

Anchors for which the following failure loads apply		Anchors according to Annex No 2*	
		Plate diameter (mm)	≥ 60
Characteristics of the MW double density boards for which the following failure loads apply		Thickness (mm)	≥ 110
		Tensile strength perpendicular to the faces (kPa)	≥ 10
Failure loads (N)	Anchors not placed at the panel joints (<i>Pull-through test</i>) dry conditions	R_{panel}	Minimum: 518 Average: 545
	Anchors not placed at the panel joints (<i>Pull-through test</i>) wet conditions	R_{panel}	Minimum: 379 Average: 400
	Anchors placed at the panel joints (<i>Pull-through test</i>) dry conditions	R_{joint}	Minimum: 582 Average: 605
	Anchors placed at the panel joints (<i>Pull-through test</i>) wet conditions	R_{joint}	Minimum: 1120 Average: 382

*plate stiffness of anchors shall be equal to or higher than 0,6 kN/mm

Table 11.

Anchors for which the following failure loads apply		Anchors according to Annex No 2	
		Supplementary plate diameter (mm)	≥ 140
Characteristics of the MW lamella for which the following failure loads apply		Thickness (mm)	≥ 50
		Tensile strength perpendicular to the faces (kPa)	≥ 80
Failure loads (N)	Anchors not placed at the panel joints (<i>Pull-through test</i>) dry conditions	R_{panel}	Minimum: 320 Average: 394
	Anchors not placed at the panel joints (<i>Pull-through test</i>) wet conditions	R_{panel}	Minimum: 257 Average: 301
	Anchors placed at the panel joints (<i>Pull-through test</i>) dry conditions	R_{joint}	Minimum: 236 Average: 291
	Anchors placed at the panel joints (<i>Pull-through test</i>) wet conditions	R_{joint}	Minimum: 265 Average: 282

The wind load resistance of the ETICS R_d is calculated as follows:

$$R_d = \frac{R_{\text{panel}} \times n_{\text{panel}} + R_{\text{joint}} \times n_{\text{joint}}}{\gamma_m}$$

where:

n_{panel} : number (per m^2) of anchors not placed at the panel joints

n_{joint} : number (per m^2) of anchors placed at the panel joints

γ_m : national safety factor

3.3.7. Render strip tensile test (ETAG 004: clause 5.5.4.1)

No performance assessed.

3.4. Protection against noise (BWR 5)

3.4.1. Airborne sound insulation (ETAG 004: clause 5.1.5.1)

No performance assessed.

3.5. Energy economy and heat retention (BWR 6)

3.5.1. Thermal resistance (ETAG 004: clause 5.1.6.1)

The thermal transmittance of the substrate wall covered by the ETICS is calculated in accordance with the standard EN ISO 6946:

$$U_c = U + \chi_p \cdot n$$

where:

$\chi_p \cdot n$ has only to be taken into account if it is greater than $0,04 \text{ W}/(\text{m}^2 \cdot \text{K})$

U_c : global (corrected) thermal transmittance of the covered wall ($\text{W}/(\text{m}^2 \cdot \text{K})$)

n : number of anchors (through insulation product) per 1 m^2

χ_p : local influence of thermal bridge caused by an anchor. The values listed below can be taken into account if not specified in the anchor's ETA:

= $0,002 \text{ W}/\text{K}$ for anchors with a stainless steel screw covered by plastic anchors and for anchors with an air gap at the head of the screw

($\chi_p \cdot n$ negligible for $n < 20$)

= $0,004 \text{ W}/\text{K}$ for anchors with a galvanized steel screw with the head covered by a plastic material ($\chi_p \cdot n$ negligible for $n < 10$)

= negligible for anchors with plastic nails (reinforced or not with glass fibres)

U : thermal transmittance of the current part of the covered wall (excluding thermal bridges) ($\text{W}/(\text{m}^2 \cdot \text{K})$) determined as follows:

$$U = \frac{1}{R_i + R_{\text{render}} + R_{\text{substrate}} + R_{\text{se}} + R_{\text{si}}}$$

where:

R_i : thermal resistance of the insulation product (according to declaration in reference to EN 13162) in $(\text{m}^2 \cdot \text{K})/\text{W}$

R_{render} : thermal resistance of the render (about $0,02$ in $(\text{m}^2 \cdot \text{K})/\text{W}$ or determined by test according to EN 12667 or EN 12664)

$R_{\text{substrate}}$: thermal resistance of the substrate of the building (concrete, brick) in $(\text{m}^2 \cdot \text{K})/\text{W}$
 R_{se} : external superficial thermal resistance in $(\text{m}^2 \cdot \text{K})/\text{W}$
 R_{si} : internal superficial thermal resistance in $(\text{m}^2 \cdot \text{K})/\text{W}$

The value of thermal resistance of each insulation product shall be given in the manufacturer's documentation along with the possible range of thicknesses. In addition, the point thermal conductivity of anchors shall be given when anchors are used in the ETICS.

3.6. Sustainable use of natural resources (BWR 7)

No performance assessed.

4. Assessment and verification of constancy of performance (hereinafter AVCP) system applied, with reference to its legal base

According to the European Commission decision 97/556/EC amended by the European Commission decision 2001/596/EC, the AVCP systems (further described in Annex V to Regulation (EU) No 305/2011) 1 and 2+ apply.

Table 12.

Product(s)	Intended use(s)	Level(s) or class(es) (Reaction to fire)	System(s)
External thermal insulation composite systems/kits (ETICS) with rendering	in external wall subject to fire regulations	A1 ⁽¹⁾ , A2 ⁽¹⁾ , B ⁽¹⁾ , C ⁽¹⁾	1
		A1 ⁽²⁾ , A2 ⁽²⁾ , B ⁽²⁾ , C ⁽²⁾ , D, E, (A1 to E) ⁽³⁾ , F	2+
	in external wall not subject to fire regulations	any	2+

⁽¹⁾ Products/materials for which a clearly identifiable stage in the production process results in an improvement of the reaction to fire classification (e.g. an addition of fire retardants or a limiting of organic material)

⁽²⁾ Products/materials not covered by footnote ⁽¹⁾

⁽³⁾ Products/materials that do not require to be tested for reaction to fire (e.g. products/materials of Classes A1 according to Commission Decision 96/603/EC)

5. Technical details necessary for the implementation of the AVCP system, as provided for in the applicable EAD

The manufacturer shall exercise permanent control of production. All the elements, requirements and provisions adopted by the manufacturer shall be documented in a systematic manner in the form of written policies and procedures. The production control system shall ensure performance constancy of the product covered by this European Technical Assessment.

The manufacturer may only use materials stated in the technical documentation of this European Technical Assessment. The factory production control shall be performed in accordance with the Control Plan which is a confidential part of the European Technical Assessment. The Control Plan was developed as a part of factory production control system.

The results of factory production control shall be recorded and evaluated in accordance with the provisions of the Control Plan.

Issued in Krakow on 05.05.2020

Signed by

A handwritten signature in blue ink, consisting of a large, stylized loop at the top and several vertical, slightly wavy lines below it.

Paweł RICHNARCZYK

Director of Łukasiewicz Research Network – Institute of Ceramics and Building Materials

Annexes:

Annex No 1 – Insulation products characteristics

Annex No 2 – Anchors characteristics

Annex No 3 – Glass fibre meshes characteristics

Annex No 1 – Insulation products characteristics

		Factory made mineral wool (MW) products according to EN 13162		
		MW board	MW double density board	MW lamella
Reaction to fire / EN 13501-1		Euroclass - A1 max. density: 130 kg/m ³		
Thermal resistance		Defined in the CE marking in reference to EN 13162 (m ² ·K)/W		
Thickness / EN 823		- 1 % or - 1 mm + 3 mm [EN 13162 - T5]	- 1 % or - 1 mm + 3 mm [EN 13162 - T5]	- 1 % or - 1 mm + 3 mm [EN 13162 - T5]
Dimensional stability under specified conditions	EN 1604	1 % [EN 13162 - DS(70,-)]	1 % [EN 13162 - DS(70,-)]	1 % [EN 13162 - DS(70,-)]
	EN 1604	-	1 % [EN 13162 - DS(70,90)]	1 % [EN 13162 - DS(70,90)]
Short-term water absorption (partial immersion) / EN 1609		EN 13162 - WS		
Long-term water absorption (partial immersion) / EN 12087		EN 13162 - WL(P)		
Water vapour diffusion resistance factor (μ) / EN 12086		EN 13162 - 1		
Tensile strength perpendicular to the faces in dry conditions / EN 1607		≥ 10 kPa [EN 13162 - TR7,5]	≥ 10 kPa [EN 13162 - TR10]	≥ 80 kPa [EN 13162 - TR80]
Shear strength / EN 12090		-	-	≥ 0,02 MPa
Shear modulus / EN 12090		-	-	≥ 1,0 MPa

Annex No 2 – Anchors characteristics

Anchor trade name	Plate stiffness (kN/mm)/ diameter (mm)	Characteristic resistance in the substrate
EJOT H1 eco EJOT H4 eco	0,6 / 60	ETA 11/0192
Ejotharm STR U 2G	0,6 / 60	ETA 04/0023
Insulation anchor Koelner TFIX-8S, Koelner TFIX-8ST	0,6 / 60	ETA 11/0144
Insulation suport TFIX-8M	1,0 / 60	ETA 07/0336
Rawlplug Facade Insulation Fixing R-TFIX-8M	1,0 / 60	ETA 17/0592
RAWLPLUG Insulation System R-TFIX-8S	0,6 / 60	ETA 17/0161
Koelner KI-10M	0,4 / 60	ETA-07/0291
KI-10N KI-10NS	0,5 / 60	ETA 07/0221
WK THERMØ8	0,6 / 60	ETA 11/0232
WK THERM S	0,6 / 60	ETA 13/0724
fischer TERMOZ 8 U	0,5 / 60	ETA-02/0019
fischer termoz CN 8 fischer termoz CN 8 R fischer termoz CNplus 8	0,6 / 60	ETA-09/0394
fischer termoz CS 8	0,6 / 60	ETA-14/0372

The use of stainless steel nail is permitted.

Additionally, anchors covered by relevant ETA can be used, provided that they meet the following requirements:

	Requirement	
	Anchors fixed through insulation product	Anchors fixed through reinforcement
Plate diameter	≥ 60 mm	≥ 60 mm
Plate stiffness	≥ 0,4 kN/mm	≥ 0,6 kN/mm

Annex No 3 – Glass fibre meshes characteristics

Mesh trade name		Description	Alkalis resistance	
			Residual resistance after ageing (N/mm)	Relative residual resistance: % (after ageing) of the strength in the as delivered state
SOLTHERM HD 158/S	ST 2924-100/7 KM	Mass per unit area: 155 g/m ² Mesh size: 4,8 x 3,7 mm	≥ 20	≥ 50
SOLTHERM HD 160/S	03-1	Mass per unit area: 160 g/m ² Mesh size: 3,6 x 3,8 mm	≥ 20	≥ 50
	SSA-1363-160 SM0.5A	Mass per unit area: 160 g/m ² Mesh size: 3,6 x 3,8 mm		
SOLTHERM HD 174/S	ST 112- 100/7KM	Mass per unit area: 170 g/m ² Mesh size: 4,0 x 3,7 mm	≥ 20	≥ 50
SOLTHERM HD 335/P	REDNET E335	Mass per unit area: 335 g/m ² Mesh size: 6,0 x 9,0 mm	≥ 20	≥ 50

Sieć Badawcza Łukasiewicz
- Instytut Ceramiki i Materiałów Budowlanych
Oddział Szkła i Materiałów Budowlanych w Krakowie
ul. Cementowa 8, 31-983 Kraków

www.icimb.pl

